

# Technical data sheet

## EGGER PerfectSense Ambiance Laminates



### Description

EGGER PerfectSense Ambiance Laminates are decorative, UV lacquer coated laminates. They have a multi-layer structure and consist of several impregnated core layers, an impregnated decor paper and a super-matt lacquer surface with partial gloss effects.

Description: EGGER PerfectSense Ambiance Laminates  
 Type of material: **HGS** (Horizontal General-purpose Standard) in accordance to EN 438-3  
 Application: horizontal surfaces with high stress

### Availability

EGGER PerfectSense Ambiance Laminates are part of the **EGGER Decorative Collection 26+** and the **EGGER Industry Pool**. They are available in selected decors from stock, according to the country-specific delivery lists.

### Technical data

Laminates with a lacquer-based surface are currently not described by or classified in the EN 438 standard. In accordance to the EN 438-3 EGGER PerfectSense Ambiance Laminates can be assigned to the standard classification **HGS** (Horizontal General-Purpose Standard). This means that the laminate can be used for horizontal applications and that subsequent postforming is not possible.

Property	Test standard	Unit or feature	Value
Resistance to surface wear*	EN 438-2	Revolutions Initial point	≥ 150
Resistance to impact by small diameter ball*	EN 438-2	N nominal thickness 0.80 mm nominal thickness 0.60 mm	≥ 20 ≥ 15
Resistance to scratching*	EN 438-2	Rating	≥ 4 <sup>1)</sup>
Thickness	EN 438-2	mm	± 0.10
Length <sup>2)</sup> and width <sup>3)</sup>	EN 438-2	mm	+ 10 / - 0
Flatness <sup>4)</sup>	EN 438-2	mm/m (max.)	60

Property	Test standard	Unit or feature	Value
Resistance to water vapour	EN 438-2	Rating (min.)	4
Resistance to dry heat (160 °C)	EN 438-2	Rating (min.)	4
Dimensional stability at elevated temperatures	EN 438-2	% max. L <sup>a</sup> T <sup>b</sup>	0.55 1.05
Resistance to wet heat (100 °C)	EN 438-2	Rating (min.)	4
Resistance to staining	EN 438-2	Rating (min.) Groups 1 and 2 Group 3	5 4
Lightfastness (Xenon arc lamp)	EN 438-2	Grey scale rating	4 to 5

\* Property is relevant for the classification of the material type.

<sup>1)</sup> ≥ 90 % continuous double circle of scratch marks clearly visible.

<sup>2)</sup> Length tolerance only applies to laminate supplied in sheets, not for rolls.

<sup>3)</sup> Tolerances for cut-to-size panels shall be agreed between EGGER and purchaser.

<sup>4)</sup> Provided that the laminate is stored in the manner and conditions recommended by EGGER.

L<sup>a</sup> = in the longitudinal direction of the fibrous sheet material (normally the direction of the longest dimension of the laminate).

T<sup>b</sup> = in the cross-longitudinal direction of the fibrous sheet material (at right angles to direction L).

## Form of delivery

PerfectSense Ambiance Laminates can be supplied as roll material or cut to size, depending on the laminate thickness. Our order-related delivery options in overview:

Options EGGER PerfectSense Ambiance Laminates	
Texture	PA – PerfectSense <u>P</u> remium <u>A</u> mbiance
Nominal thickness – sheet form	0.60 and 0.80 mm
Nominal thickness – roll format	0.60 mm
Maximum length – sheet form	5,600 mm; 50 mm grid
Minimum length – sheet form	800 mm; 50 mm grid
Standard length	2,464; 2,800; 3,050 and 4,100 mm
Roll length	200 and 400 m
Standard width	1,310 mm
Core diameter	150 mm
Protection film	<u>without</u> protective film as standard

## Technical application note

The very matt PerfectSense Premium Ambiance surface is based on a UV lacquer finish with anti-fingerprint properties. The lacquer surface has partially “no texturing”, so signs of wear may appear when subjected to mechanical stress. With medium to dark solid and printed decors, traces of use are more noticeable than with light decors. This is not a functional impairment of the surface, but an impairment based on visual aspects.

Slight colour deviations in the same product are possible due to tolerances in the primary materials used. Components that are used next to each other should therefore be checked for colour uniformity. A deviation in colour and surface between the EGGER reference colour sample and the customer's test piece is permissible in accordance with EN 438.

Due to the production that differs by product, colour and surface differences can also occur between different products (e.g. faced board, laminate, edging) with the same decor-texture combination. For an accurate representation of the colour, order a sample in the relevant product.

## Care and cleaning recommendation

EGGER PerfectSense Ambiance Laminates do not require any special care due to their resistant and hygienic, dense surfaces. The surfaces are generally easy to clean. Do not use sanitary cleaners or detergents with abrasive components, as using such cleaners may lead to changes in the degree of gloss and/or scratch the material. Refatting agents, as used in some cases in plastic cleaners, also lead to changes in the gloss level and, in order to maintain anti-fingerprint properties, must be removed without residue from the surface.

For detailed information, please refer to the leaflet "Cleaning and care recommendations for EGGER product surfaces".

## Additional documents / Product information

You will find further information in the following documents:

- » Processing instructions "EGGER Laminates"
- » Technical leaflet "EGGER Laminates balancer"
- » Technical leaflet "Resistance to chemicals EGGER Laminates"
- » Technical leaflet "Cleaning and care recommendations for EGGER product surfaces"

### Provisional note:

This technical data sheet has been carefully drawn up to the best of our knowledge. The information provided is based on practical experience, in-house testing and reflects our current level of knowledge. It is intended for information only and does not constitute a guarantee in terms of product properties or its suitability for specific applications. We accept no liability for any mistakes, errors in standards, or printing errors. In addition, technical modifications may result from the continuous development of EGGER PerfectSense Ambiance Laminates, as well as from changes to standards and public law documents. The contents of this technical data sheet should therefore not be considered as instructions for use or as legally binding. Our General Terms and Conditions apply.